

QUICKFLOOR 300

ALIPHATIC HIGH PERFORMANCE FLOORING SYSTEM

QuickFloor 300 is a solvent free, low odor, high performance, rapid curing flooring product based on the latest polyaspartics technology.

QuickFloor 300 provides excellent color stability, gloss retention and chemical resistance combined with a longer working time and higher elongation. **QuickFloor 300** can be applied airless spray, low pressure plural component, roller, squeegee or a notched trowel. With a tack free time of app. 90 min re-use times are incredibly short saving customers valuable down time.

QuickFloor 300 can be applied as pigmented top coat over VIP's decorative flooring options and elastomeric coating systems.

USES

- As seamless rapid application, 1 product, 1 application, commercial, decorative and industrial flooring system
- Aircraft hangers
- Warehouse flooring
- Restaurants and kitchens, breweries, wine cellars, bakery shops
- Retail shops and shopping malls
- Hospital flooring
- Car park decks

FEATURES

- Solvent free
- Extremely fast cure and re-use times
- Remains flexible
- Very good hiding power when pigmented
- Excellent colour and gloss retention
- Cures to a very clear finish when not pigmented
- Excellent abrasion resistance
- Resistant to most chemicals, solvents, acids and caustics
- Can be used for in-door and outdoor applications
- Stable over a wide temperature range
- High flexibility and impact resistance compared to traditional epoxy systems

SURFACE PREPARATION

All cementitious substrates must be structurally sound. Surfaces must be entirely free of oil, grease, paint, dust, curing agents, re-release agents or other surface contamination. Loose or unsound material should be removed. Sweep and vacuum to remove all dust and debris.

Steel substrates should be prepared to a class 2 ½ near white blast finish with a surface profile of 80 microns.

Mask all adjacent surfaces and protect the surrounding area from overspray. Do not apply unless the substrate temperature is 3°C or greater than dew point.

QUICKFLOOR 300

ALIPHATIC HIGH PERFORMANCE FLOORING SYSTEM

APPLICATION INSTRUCTIONS

Thoroughly power stir the B-side component before combining the A and B components. Combine the A side and B side components and power stir again before applying to substrate.

The mixing ratio of comp. A to comp. B is 1:1 by volume. To ensure full physical characteristics are achieved within the finished coating use graduated beakers / containers to ensure accurate 1:1 by volume mixing of component A and component B.

QuickFloor 300 can be applied by roller, squeegee or notched trowel/rake.

When applying two or more coats allow each coat to dry completely before applying subsequent coats. If recoat window is exceeded, sand slightly to produce a profile, wipe with acetone and then apply the next coat.

Use a 8 – 13 mm Nap Mohair roller when rolling **QuickFloor 300**.

When applying **QuickFloor 300** with a squeegee or notched trowel the floor should be back rolled using spiked roller to assist in de-airing the coating.

ADDITIONAL NOTES

Please note that the tack free and curing times of **QuickFloor 300** are influenced by the environmental conditions at the time of application. Heat and humidity will accelerate the reactivity and curing of **QuickFloor 300**. In hot and humid environments only mix small amounts of product at a time to enable full application of mixed product.

In cold environments the tack free time and cure times can be extended considerably especially in environments less than 10°C.

QUICKFLOOR 300

ALIPHATIC HIGH PERFORMANCE FLOORING SYSTEM

PROCESSING PROPERTIES

INFORMATION ABOUT THE USE OF THE PRODUCT

	DATA
Mixing ratio of Comp. A to Comp. B	1:1 by volume
Material consumption L / m ²	0.25L @ 250 µm (Will vary based on substrate)
Recommended thickness [µm]	150 – 250 per coat
Numbers of coats	Depends on application requirements
Pot life at 20°C [min.]	60 - 80
Waiting time between the single layers* [h]	1
Tack free time* [h]	1
Pedestrian traffic after* [h]	Light: 2 - 4 Heavy: 5 - 8
Curing* (Normal loading) [h]	8 - 12
Temperature range for application (ambience) [°C]	+5 - +50
Temperature range for application (substrate) [°C]	
Over coat window (h)	8
Maximal relative air humidity for application [%]	98
Recommended coating thickness [µm]	150 - 750

QUICKFLOOR 300

ALIPHATIC HIGH PERFORMANCE FLOORING SYSTEM

PHYSICAL PROPERTIES

INFORMATION ABOUT THE USE OF THE PRODUCT

	DATA	
Chemical Base	–	Comp. A: HDI-Prepolymer Comp. B: Mod. Polyaspartics/Polyurea
VOC-content	DIN EN ISO 11890-1 / ASTM D-1259	0%
Solids content	DIN EN 827 / ASTM D-2697	100%
Color	–	RAL 5015, RAL 5005, RAL 7035, RAL 7005, RAL 1002, RAL 9010
Viscosity [mPa*s] @ 25° C	DIN EN ISO 2884-2 / ASTM D-4878	Comp. A: 1.100 - 1.500 mPa*s Comp. B: 40.000 - 50.000 mPa*s Mix: 3.000 - 3-500 mPa*s
Density [g/cm³] @ 20° C	DIN EN ISO 2811-1 / ASTM D-1217	Comp. A: 1,10 - 1,14 g/cm³ Comp. B: 1,29 - 1,33 g/cm³ Mix A+B: 1,22 g/cm³
Tensile strength [MPa]	ISO 37	≥ 11
Tension 100% [MPa]		≥ 10,6
Elongation at break [%]		≥ 105
Hardness [Shore A]	DIN ISO 48-4	85 ± 5
Hardness [Shore D]	DIN 53505	60 ± 5
Rebound resilience [%]	DIN53512	≥ 10,5
Tear growth resistance [N/mm]	DIN ISO 34-1	≥ 6,0
Taber Abrasion [mg]	ASTM D-4060	< 35 (Wheel CS17 / 1.000g / 1000 cycles)
Colour fastness T= 100°C 60 W/m² 15000 kJ/m²	DIN EN ISO 105-B06	After approx. 70 hours: ΔE*= 2,44 No chalking, no discolouration, no cracking and no blistering.
Colour fastness 8h QUV/60°C + 4h condensati-on/50°C UV-lamp: type A (340nm)	ASTM G154a / ISO 4892	After approx. 500 hours: No chalking, no discolouration, no cracking and no blistering.
Pull off strength [N/mm²]	DIN EN ISO 4624 / ASTM D-4541	Concrete: ≥ 1,5
Liquid Impingement Erosion Test conditions: Water jet 135m/s	ASTM G-73-10	Wear resistant up to 240 min. against liquid impingement erosion
Max. Process temp. [°C]	–	Wet: 60 Dry: -20 to +120 Peak temperature dry: 140
Storage conditions [°C]	DIN EN 12701 / ASTM	10 – 30 (in closed original drums, stored at dry and well ventilated place; beware of freezing)
Shelf life	–	Approx. 12 months
Antibacterial activity	BS ISO 22196	1,8 : Results „borderline“ (96,8-99,0%) – (Bacteria: S.aureus) 2,0 : Results „borderline“ (96,8-99,0%) – (Bacteria: E.coli)

QUICKFLOOR 300

ALIPHATIC HIGH PERFORMANCE FLOORING SYSTEM

IMPORTANT NOTE

All test results and timings provided are based on tests carried out in laboratory conditions. Substrate and atmospheric temperature, humidity, condition and application thickness will all influence these results and therefore they must be used as a guide only.

PACKING

20 Litre drums

STORAGE / SHELF LIFE

When stored in dry conditions out of direct sunlight in original unopened packaging, this product has a shelf life of approximately 12 months from the date of manufacture. Avoid storing product in temperatures above 35C as this may reduce the products shelf life.

Drums, including empty drums should always be kept tightly sealed. During storage and processing, avoid any contamination with other liquids and moist air which may cause solids to form leading to blockages in filters, pumps and/or pipelines.

CLEANING

Prior to curing, tools may be cleaned with cleaning solvents. Once hard, by mechanical means only.

TECHNICAL SERVICES

Detailed technical assistance and further information regarding this system and its relevant application specifications are available from VIP Technical Services.

HEALTH AND SAFETY

Respiratory protection is mandatory for all sprayers and workers in the immediate vicinity of spray operations. A copy of the Model Respiratory Protection Program, developed by API is available at www.polyurethane.org and from the supplier.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, at the time of printing. However the accuracy, completeness and repeatability of said tests results are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and tests, to determine the suitability of the product / system for his own particular project and application. User assumes all risk and liability resulting from his use of this product / system. We do not suggest or guarantee that any hazards listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or incorrect use of the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and standard application procedures. Test performance results were obtained in a controlled environment and the manufacturer makes no claim that these tests or any other tests, accurately represent all environments.

ISSUE DATE: JUNE 2024

This technical specification supersedes all previous data sheets.